

AMENDMENT NO. 1 MARCH 2018
TO
IS 13606 : 2013 SYNTHETIC SULPHOCHLORINATED
FATLIQUORS FOR LEATHER PROCESSING —
SPECIFICATION

(First Revision)

(Page 1, Table 1) — Substitute the following for the existing table:

Table 1 Chemical Requirements
(Clause 4.2)

SI No.	Characteristic	Requirement	Method of Test, Ref to
(1)	(2)	(3)	(4)
i)	pH of 10 percent solution	6.5 – 7.0	A-2
ii)	Water content, percent by mass, <i>Max</i>	40.0	A-3
iii)	Total fatty matter, percent by mass, <i>Min</i>	60.0	A-4
iv)	Total sulphur, percent by mass, <i>Min</i>	4.0	A-5
v)	Total chlorine, percent by mass, <i>Min</i>	22.0	A-6
vi)	Total ash, percent by mass, <i>Max</i>	4.0	A-7
vii)	PCP content ¹⁾ , mg/kg, <i>Max</i>	5.0	A-8
viii)	Total free formaldehyde, ppm, <i>Max</i>	50.0	CHD 17 (10756)F ²⁾

¹⁾ Calculated on moisture-free basis.
²⁾ Document under printing.